

Ressi EPO Crack Fill LV is a three-part solvent free epoxy low viscosity crack filling system designed over low viscosity Bisphenol A based Resins and Polyamide based high strength Epoxy based hardeners. **Ressi EPO Crack Fill LV** is designed to fill both hairline and thick cracks from 25mm wide to 75mm Deep. Due to its high level of flow and high compressive strength this material is compatible with most concrete floorings where high wear is prevalent. This impact resistant crack filler can be applied using a variety of tools like trowels and other materials. **Ressi EPO Crack Fill LV** is also suitable for a variety of substrates such as metal, wood, ceramic, concrete, textile, glass, leather etc.

ADVANTAGES

- ✓ Easy to apply and cleanup.
- ✓ Triple the strength of concrete.
- ✓ Flexible and resilient.
- ✓ Cures to dense joint free surface.
- ✓ Good chemical resistance.

AREAS OF APPLICATION

Ressi EPO Crack Fill LV is an ideal Crack filler for the repair of concrete floors, floor joint repairs, levelling rough surfaces prior to the application of epoxy flooring and crack repair of general cementitious floorings. **Ressi EPO Crack Fill LV** can also be used over various substrates like metal and wood subject to material compatability and proper onsite trials of the material.

SURFACE PREPARATION

All loose particles and oil should be cleaned off the surface prior to the application. Minor hairline cracks need to be opened to a minimum width of 12mm prior to treating the floor surface with **Ressi EPO Crack Fill LV**

APPLICATION & MIXING

It is Recommended to slowly add Part B over Part A (Resin over hardener). And mix it with a slow speed drill for at least 2 minutes. It is to be ensured that the speed of the drill mix should not exceed 400 rpm. After the base and hardener have mixed properly, filler can be added as per requirement. It is to be noted that the quantity of fillers can be adjusted as per the requirement of the site. The higher the quantity of the filler, the more viscous the material. Once the material is mixed properly, depending upon the viscosity, it can either be poured into the crack or applied by using an appropriate trowel or scrapper over the cracked surface.

TECHNICAL PROPERTIES

Component	-	Three-part System: Part A: Resin Part B: Hardener Part C: Filler
Color	-	Brownish (After Mixing)
Pot life (300g mix) @ 25°C	Theoretical	40 – 60 minutes
Mix Ratio	-	1 Part Resin (Part A) 0.8 Part Hardener (Part B) 20 Parts Filler (Part C)
Cure time	-	12 Hours
Full Cure	-	7 Days
Tensile Strength (PSI)	ASTM D638	1500 – 2000 (Depending on filler ratio)
Compressive Strength (PSI)	ASTM D695	6000 – 12000 (Depending on Filler ratio)

Typical Properties under laboratory conditions

SHELF LIFE

Ressi EPO Crack Fill LV has a shelf life of 6 months if stored under dry and cool conditions.

PACKAGING

Ressi EPO Crack Fill LV is supplied in the following packaging

2.18KG: Part A 100g (Liquid Resin)
Part B 80g (Liquid Hardener)
Part C 2 KG (Filler Powder)

21.8KG: Part A 1KG (Liquid Resin)
Part B 800g (Liquid Hardener)
Part C 20KG (Filler powder)

HEALTH AND SAFETY

The packed material of Ressi EPO Crack Fill LV is regarded as non-hazardous for transportation. Once opened extreme temperatures may cause the material to be flammable. Do not reuse bags, containers, and packaging materials. It is recommended to dispose off the packaging as per local rules and regulations. Gloves and suitable masks can be worn during application. Please refer to MSDS of the product for further health and safety information.



PRINTED



UNIVERSAL



PRINTED



UNIVERSAL

NOTE:

If printed packaging not available, neutral packaging with label. Lot number and manufacturing date to be stamped at the back of each packaging.